



**KAPCI**  
COATINGS

**Technical Data Sheet**

Issue date January 2024

for professional use only

## Kapci Top 730 - Matt

### Product Description:

Kapci Top 730 is high quality matt topcoat based on modified acrylic emulsion with excellent washability, hiding power and whiteness. It is used for interior surfaces. Kapci 730 is recommended for application over bricks, plaster, concrete and asbestos cement sheets.

### Product Features:

- Alkali resistant
- Washable (up to 10000 cycles)
- Excellent non-yellowing properties
- Excellent hiding power
- High whiteness
- Dirt pick-up resistant
- Excellent leveling

### Physical Properties

<b>Color</b>	White and colored
<b>Viscosity</b>	37±3 Krebs
<b>Solid content</b>	56±3%
<b>Density</b>	1.52±0.03gm/cm <sup>3</sup>
<b>Gloss</b>	Matt
<b>Coverage</b>	7-10 m <sup>2</sup> /kg (Dry film thickness 40-45µ)

### Surface preparation

- Remove all loose, defective paint or powdery residues or dust.
- Repair cracks, uneven surfaces with a suitable fillers or surfacer.
- Smoothen the putty / filler areas with sand paper.
- Surfaces to be painted must be cleaned thoroughly and dry and free from contaminations, grease and other foreign matters.
- Avoid painting when the moisture content and alkalinity of the walls are still high.
- **For new surface** Apply Kapci Sealer 751 in one coat; then apply Kapci Putty 750, then apply again 751
- **For previously painted surfaces with alkyd paints** sand, remove dust then apply Super matt 766 then Sealer 751
- **For previously painted surfaces with emulsion paints**, wash surface and apply Kapci Sealer
- Apply Kapci Matt 730 in two coats after dilution with water (15 % dilution) to reach the application viscosity;

---

**IMPORTANT NOTE:** These TDS are for information purposes only without any obligation as we do not have control over the quality and conditions of the surface or application.



# KAPCI COATINGS

## Application

### Tools for application

Roller	Brush	Spray
Recommended	Recommended to paint corners and edges.	Use airless spray or conventional spray.
		<b>Guiding data for airless spray</b> Nozzle tip 0.015–0.021" Spray angle degrees 20°-60° Pressure at nozzle 140 - 190 kg/cm <sup>2</sup> (2100 psi)



### Drying time at 25 °C & 60% R.H

Initial drying time	1h
Recoating time	4h
Final drying time	6h

### General Notes

1. Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.
2. Recommended data given is, for recoating with the same generic type of paint.
3. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
4. The surface should be dry and free from any contamination prior to application of the subsequent coat.
5. Cleaner of application Tools is water

### Shelf Life and Storage

Two years from production date if stored in original sealed container at normal temperature. Keep away from direct sun light.

### Health and Safety

1. For full Health and Safety information, refer to the Material Safety Data Sheet (MSDS).
2. Observe the precautionary notices displayed on the container.
3. Goggles and suitable protective equipment must be worn while using these products.
4. Good ventilation must be provided in the working environment.

---

**IMPORTANT NOTE:** These TDS are for information purposes only without any obligation as we do not have control over the quality and conditions of the surface or application.