



KAPCI
COATINGS

Technical Data Sheet

Issue date January 2025

for professional use only

WS 690 – White Nitrocellulose Surfacer

Product properties

WS 690 is a fast drying, easy to sand White nitrocellulose surfacer having excellent filling properties. It is used for wooden surfaces not exposed to mechanical, chemical, or thermal effects. Kapci WS690 can be used for furniture, wooden articles and interior woodwork including cupboards, shelves, door frames, window frames, partitions, etc.

Theoretical coverage: 5-7 m²/l per coat


Products for application

WS 690 NC Surfacer

Kapci 526 NC Thinner

Substrate and surface preparation

Sand the surface of solid wood with P180 or P120 sanding paper. For MDF, plywood or veneer, use finer grit paper P220 or P180. Blow off dust and wipe off contaminants (grease, oil, etc.) prior to applying Kapci WS 690 NC surfacer.



Mixing ratio by volume:
100:100

100% Kapci WS690 NC Surfacer
100% max Kapci 526 NC thinner



Application viscosity:
18-20 s (F4/20°C)



Spray gun tips:

	Spray Nozzle	Inlet pressure	Atomization pressure
Compliant	1.6-1.8	2 bars (26- 29 psi)	
HVLP	1.6-1.8	2 bars (26- 29 psi)	0.7bar (8-10 psi)
Conventional	1.6-1.8	3-3.5 bar (45-50 psi)	

IMPORTANT NOTE: These TDS are for information purposes only without any obligation as we do not have control over the quality and conditions of the surface or application.




KAPCI
COATINGS



Number of coats:

Apply 2-3 single coats
Total dry film thickness 40-50 microns



Flash off time:

5 min between coats



Drying time at 25 °C:

Dust free: 20 – 30 min
Dry to Sand 2-3 h

Other tips

1. Practical coverage depends on several factors including shape, roughness and porosity of the object to be painted, spraying equipment used, application methods, application conditions, film thickness, etc.
2. For best results, it is always recommended to test the products on scrap pieces of wood before start paint job.

Shelf life

3 years from production date stored in original packaging at normal conditions.

Health and Safety

1. For full Health and Safety information please refer to the Material Safety Data Sheet.
2. Observe the precautionary notices displayed on the container.
3. Good ventilation must be provided in the working environment.

IMPORTANT NOTE: These TDS are for information purposes only without any obligation as we do not have control over the quality and conditions of the surface or application.