



KAPCI
COATINGS

Technical Data Sheet

Issue date January 2025

for professional use only

Kapci 200 NC Paint


Product description

Kapci 200 is a high gloss topcoat based on nitrocellulose resin. It delivers very fast drying and good coverage. It is used for partial repairs both indoor and outdoor. The product is not recommended for all car repair.

Substrates

Kapci 200 topcoat can be applied over old paints in solid conditions, NC putties, and 1K and 2K fillers. The surface should be properly prepared and degreased prior to painting.

Application



Mixing ratio by volume:
100:100

100% Kapci 200 Paint
100% Kapci 526 NC thinner

(1:1)



Use mixing ruler



Application viscosity:
18-20 s (F4/20°C)



Spray gun tips:


	Spray Nozzle	Inlet pressure	Atomization pressure
Compliant	1.3-1.4	2 bars (26- 29 psi)	
HVLP	1.3-1.4	2 bars (26- 29 psi)	0.7bar (8-10 psi)
Conventional	1.3-1.4	3-3.5 bar (45-50 psi)	

Refer to the spray gun manufacturer's recommendation.



Number of coats:

Apply 2-3 single coats (i.e., apply until get opacity).
Total dry film thickness 40-50 microns



Flash off time:

3- 5 min between coats

IMPORTANT NOTE: These TDS are for information purposes only without any obligation as we do not have control over the quality and conditions of the surface or application.



KAPCI
COATINGS



Drying time:

Dry to handle: 30 min/20°C

Health and Safety

1. For full Health and Safety information, refer to the Material Safety Data Sheet (MSDS).
2. Observe the precautionary notices displayed on the container.
3. Goggles and suitable protective equipment must be worn while using these products.
4. Good ventilation must be provided in the working environment.