



KAPCI
COATINGS

Technical Data Sheet

Issue date January 2025

for professional use only

Kapci 850 Synthetic Primer


Product description

Kapci 850 is a 1K fast drying synthetic primer with good anticorrosion properties and adhesion over steel. Kapci 850 can be recoated with 1K topcoats.

Substrates

Kapci 850 Synthetic Primer can be applied over steel. For maximum durability steel should be prepared by blast cleaning/sanding. Alternatively, sand using P80-P180 sanding machine discs. Thoroughly degrease with Kapci 606 degreaser.

Application



Mixing ratio by weight:

100:30

100 % Kapci 850 Synthetic Primer
30 % Kapci 525 NC Thinner



Spraygun tips:

	Spray Nozzle	Inlet pressure	Atomization pressure
Compliant	1.7-1.8mm	2 bars (26- 29 psi)	
HVLP	1.7-1.8mm	2 bars (26- 29 psi)	0.7bar (8-10 psi)
Conventional	1.7-1.8mm	3-3.5 bar (45-50 psi)	

Refer to the spray gun manufacturer's recommendation.



Number of coats:

Apply 2 normal coats.

Total dry film thickness 50-60 microns.



Flash off time:

Approximately 10-15 min/20°C between coats.



Drying time at 20°C: 1 h

Dry to recoat: after minimum 1 h at 20°C



KAPCI
COATINGS

General notes

Degreasing

For bare metal use Kapci 606 Degreaser.

Note: Kapci 606 is recommended for bare metal. However, in a case of a lack of Kapci 606, Kapci 605 Degreaser can be helpful as well.



- Saturate a clean cloth with Kapci 606 Degreaser;
- Apply to areas to be painted and adjacent panels;
- Wipe off surplus degreaser with a clean dry cloth; do not allow the degreaser to dry on the surface.

Recoatable

Kapci 850 is recoatable after minimum 1 hour at 20°C

Health and Safety

1. For full Health and Safety information please refer to Material Safety Data Sheet (MSDS).
2. Observe the precautionary notices displayed on the container.
3. Goggles and suitable protective equipment must be worn while using these products.
4. Good ventilation must be provided in the working environment.